



**Product Data Sheet &
General Processing Conditions**

**RTP 1505-55D
Polyether-Ester Block Copolymer
(TEEE/COPE)
Glass Fiber**

PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

PERMANENCE	English	SI Metric	ASTM TEST
Primary Additive	30 %	30 %	
Specific Gravity	1.42	1.42	D 792
Molding Shrinkage 1/8 in (3.2 mm) section	0.0015 - 0.0021 in/in	0.15 - 0.21 %	D 955

MECHANICAL

Impact Strength, Izod notched 1/8 in (3.2 mm) section	6.7 ft-lbs/in	358 J/m	D 256
unnotched 1/8 in (3.2 mm) section	No Break	No Break	D 4812
Tensile Strength	7350 psi	51 MPa	D 638
Tensile Elongation	9.2 %	9.2 %	D 638
Tensile Modulus	0.36 x 10 ⁶ psi	2482 MPa	D 638
Flexural Strength	10200 psi	70 MPa	D 790
Flexural Modulus	0.34 x 10 ⁶ psi	2344 MPa	D 790
Hardness Shore D, instantaneous	65	65	D 2240

PROPERTY NOTES

Data herein is typical and not to be construed as specifications.
Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

GENERAL PROCESSING FOR INJECTION MOLDING

	English	SI Metric
Injection Pressure	10000 - 15000 psi	69 - 103 MPa
Melt Temperature	410 - 460 °F	210 - 238 °C
Mold Temperature	70 - 100 °F	21 - 38 °C
Drying	2 - 4 hrs @ 220 °F	2 - 4 hrs @ 104 °C
Moisture Content	< 0.10 %	< 0.10 %

PROCESSING NOTES

Desiccant Type Dryer Required.

14 Dec 2004 RLR

This information is intended to be used only as a guideline for designers and processors of modified thermoplastics. Because design and processing is complex, a set solution will not solve all problems. Observation on a "trial and error" basis may be required to achieve desired results.

Data are obtained from specimens molded under carefully controlled conditions from representative samples of the compound described herein. Properties may be materially affected by molding techniques applied and by the size and shape of the item molded. No assurance can be implied that all molded articles will have the same properties as those listed.

No information supplied by RTP Company constitutes a warranty regarding product performance or use. Any information regarding performance or use is only offered as suggestion for investigation for use, based upon RTP Company or other customer experience. RTP Company makes no warranties, expressed or implied, concerning the suitability or fitness of any of its products for any particular purpose. It is the responsibility of the customer to determine that the product is safe, lawful and technically suitable for the intended use. The disclosure of information herein is not a license to operate under, or a recommendation to infringe any patents.